

ROTT TEST DATA
Thermiculite 835 Spiral Wound
Class 150, 5 x 5.875 x 0.175 in.

Gb	2,120 psi
a	0.190
Gs	49 psi
T _p MIN	42
T _p MAX	79,395
S ₁₀₀	5,083 psi
S ₁₀₀₀	7,868 psi
S ₃₀₀₀	9,691 psi
S ₁₀₀₀₀	12,178 psi

Design Properties

m	3.0
Y	10,000 psi

Thermiculite®

INNOVATIVE. VERSATILE. COMPLETE.



CRITICAL SERVICE SERIES
Thermiculite® 835 Spiral Wound,
high temperature filler material for
spiral wound gaskets.

